

255 x 125 Square Channel

Date Created: 10/05/18



Standard Grey Channel

Marshall's uses hydraulic pressing in the manufacture of its standard natural kerb, channels and edgings. The result is the durability and consistent long-term performance you would expect from Marshall's with a functional unit of this type.

These precision-manufactured products are available in many different shapes and profiles to fulfil a wide range of design requirements.

Bullnose and Square channels are typically used as a spacer between the kerb and the carriageway or for off road parking and lay-bys, while Dished channels provide an aid to drainage. Bullnose, Round Top and Flat Top edging is mostly used along footpath edges.

Download our brochure to explore the full range.

DESCRIPTION

| | |
|-----------------------------------|---|
| Appearance | Solid unit with pimple surface |
| Manufacturing Process | Hydraulically pressed concrete |
| Base Raw Material | Concrete |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 1340 : 2003 |
| CE Marking/DOP | https://www.marshall's.co.uk/dop |
| NBS Specification | Q10 10 |

255 x 125 Square Channel

Date Created: 10/05/18

PHYSICAL PROPERTIES

| | |
|------------------------------------|---|
| Work Dimensions (mm) | 255 x 125 x 915 |
| Tolerances on Work Dimensions (mm) | Length ± 3 mm, width ± 3 mm, thickness ± 3 mm |
| Abrasion Resistance (mm) | ≤ 23 mm (Wide Wheel Abrasion Test) |
| Durability (Freeze-thaw) | ≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ² |
| Material Density | 2300 kg/m ³ (typically) |
| Slip/Skid Resistance (polished) | Mean polished skid resistance value (PSRV) : > 45 |
| Slip/Skid Resistance (unpolished) | Mean unpolished skid resistance value (USRV) : > 45 . |
| Transverse/FlexuralSplit/Breaking | Characteristic bending strength of 3.5 MPa with no individual result less than 2.8 MPa |

SPECIFICATION

| | |
|---------------------------|---|
| Approx unit weight (kg) | 64 |
| Emission of Asbestos | No content |
| External Fire Performance | Deemed to satisfy. See commission decision 2000/553/ECU |
| Reaction to fire | Class A1, see commission decision 2000/605/EC |

APPLICATION

| | |
|-------------|--|
| Suitability | Laid in accordance with BS 7533-6 : 1999 |
|-------------|--|

FURTHER INFORMATION

| | |
|------------------------|--|
| Cleaning & Maintenance | Information regarding the cleaning & maintenance of this product may be obtained on request |
| Efflorescence | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking |
| Weathering | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures. |
| Product Evolution | The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice |
| Contact Us | For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233 |