


Bullnosed Edging 50 x 150 x 914



Grey Edging &
Channel

Marshall's uses hydraulic pressing in the manufacture of its standard natural kerb, channels and edgings. The result is the durability and consistent long-term performance you would expect from Marshall's with a functional unit of this type.

DESCRIPTION	
Appearance	Standard natural concrete unit
Manufacturing Process	Hydraulically pressed concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1340 : 2003
NBS Specification	Q10 10



Bullnosed Edging 50 x 150 x 914

PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Width ± 3 mm, height ± 3 mm, length ± 3 mm
Abrasion Resistance (mm)	≤ 23 mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²
Material Density	2300 kg/m ³ (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45 .
Bending Strength MPa	Characteristic bending strength of 3.5 MPa with no individual result less than 2.8 MPa

SPECIFICATION

Approx unit weight (kg)	16
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC
Installation	Laid in accordance with BS 7533-102 : 2025

SUSTAINABILITY

Carbon Footprint	Available on Request
------------------	----------------------

SUPPLY

Av. pack weight (kg)	626
----------------------	-----

FURTHER INFORMATION

Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

