Landscape House, Premier Way, Lowfields Business Park, Elland, HX5 9HT Tel: 03704 112233 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 25/04/24

Conservation X Textured Step 350 x 150 x 1000





Marshalls' Single Solid Concrete Step Units are manufactured in concrete with lightly textured granite aggregates, making them a durable and attractive option for any urban environment. The Single Solid Concrete Step Units come equipped with 55mm wide visibility strips set 35mm from the edge of the kerb horizontally and vertically. These standard strip colours meet the BS 8300 light reflectance values (LRV) standards*. Available in 2 colours, the product is a versatile complementary step unit with numerous paving and block paving ranges.

DESCRIPTION	
Appearance	Solid unit with textured surface
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1339 : 2003
UKCA Marking/DOP	E Exempt
NBS Specification	Q25 315

















Landscape House, Premier Way, Lowfields Business Park, Elland, HX5 9HT Tel: 03704 112233 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 25/04/24

Conservation X Textured Step 350 x 150 x 1000

Work Dimensions (mm) Nominal Dimensions (mm) Nominal Dimensions (mm) Tolerances on Work Dimensions (Class 2 tolerances to all dimensions as standard, Length ±2mm, width ±2mm, thickness ±3mm Abrasion Resistance (mm) Surability (Freeze-thaw) Durability (Freeze-thaw) Silip/Skid Resistance (polished) Silip/Skid Resistance (unpolished) Mean polished skid resistance value (PSRV): > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV): > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content Deemed to satisfy. See commision decision 2000/553/ECU Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0		
Nominal Dimensions (mm) Tolerances on Work Dimensions (mm) Class 2 tolerances to all dimensions as standard, Length ±2mm, width ±2mm, thickness ±3mm Abrasion Resistance (mm) Surability (Freeze-thaw) Durability (Freeze-thaw) Silp/Skid Resistance (polished) Silp/Skid Resistance (polished) Mean polished skid resistance value (PSRV): > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV): > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/653/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	PHYSICAL PROPERTIES	
Tolerances on Work Dimensions (mm) Class 2 tolerances to all dimensions as standard, Length ±2mm, width ±2mm, thickness ±3mm Abrasion Resistance (mm) Summability (Freeze-thaw) Durability (Freeze-thaw) Summability (Freeze-thaw) Sum	Work Dimensions (mm)	348 x 148 x 1000
dimensions as standard,Length ±2mm, width ±2mm, thickness ±3mm Abrasion Resistance (mm) Durability (Freeze-thaw) Durability (Freeze-thaw) Slip/Skid Resistance (polished) Slip/Skid Resistance (unpolished) Mean polished skid resistance value (PSRV): > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV): > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Nominal Dimensions (mm)	350 x 150 x 1000
Test) Durability (Freeze-thaw) ≤ 1.0 kg/m² as a mean with no individual value > 1.5 kg/m² Material Density 2300 kg/m³ (typically) Slip/Skid Resistance (polished) Mean polished skid resistance value (PSRV) : > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV) : > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Tolerances on Work Dimensions (mm)	dimensions as standard,Length ±2mm, width ±2mm, thickness
individual value > 1.5 kg/m² Material Density 2300 kg/m³ (typically) Slip/Skid Resistance (polished) Mean polished skid resistance value (PSRV) : > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV) : > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Abrasion Resistance (mm)	•
Slip/Skid Resistance (polished) Mean polished skid resistance value (PSRV): > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV): > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) Emission of Asbestos No Content Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Durability (Freeze-thaw)	
value (PSRV) : > 45 Slip/Skid Resistance (unpolished) Mean unpolished skid resistance value (USRV) : > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Material Density	2300 kg/m³ (typically)
value (USRV) : > 45 Thermal Conductivity (K value) Design data as defined to BE EN 13369:2013 Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Slip/Skid Resistance (polished)	•
Bending Strength MPa Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Slip/Skid Resistance (unpolished)	
4.0 MPa with no individual result less than 3.2 MPa SPECIFICATION Approx unit weight (kg) 126 Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Thermal Conductivity (K value)	9
Approx unit weight (kg) Emission of Asbestos No Content External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Bending Strength MPa	4.0 MPa with no individual result
Emission of Asbestos External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	SPECIFICATION	
External Fire Performance Deemed to satisfy. See commision decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Approx unit weight (kg)	126
decision 2000/553/ECU Reaction to fire Class A1, see commision decision 2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Emission of Asbestos	No Content
2000/605/EC SUSTAINABILITY Breeam These units can achieve an "A" rated system when used in conjunction with the correct sub- base components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	External Fire Performance	
Breeam These units can achieve an "A" rated system when used in conjunction with the correct sub- base components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	Reaction to fire	
"A" rated system when used in conjunction with the correct subbase components Carbon Footprint 0 SUPPLY Packaging All packs are suitable for crane off-	SUSTAINABILITY	
SUPPLY Packaging All packs are suitable for crane off-	Breeam	"A" rated system when used in conjunction with the correct sub-
Packaging All packs are suitable for crane off-	Carbon Footprint	0
Packaging All packs are suitable for crane off-	SUPPLY	
	Packaging	·

FURTHER INFORMATION	
Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233













