

## Hawks View Sandstone



A striking dual-colour brown and grey sandstone, Hawks View features natural banding, making every paver unique. Hawks View Indian Sandstone is offered in four different finishes allowing the creation of a variety of beautiful designs and blends in one scheme. Its impressive strength and high load-bearing capacity means it is particularly suited to mixed-use areas. This versatile sandstone is available in all applications and due to the size of the quarried block, it is perfect for larger items such as bespoke street furniture.

All our sandstones are fully tested to the appropriate standards in the UK and are all UKCA marked in accordance with the latest legislation.

DESCRIPTION	
Appearance	Grey to Brown Sandstone
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry Location	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012, BS EN 1342 : 2012 & BS EN 1343 : 2012
Petrographical Description	Light beige bluish grey and light reddish brown fine grained Sandstone
UKCA Marking/DOP	<a href="http://www.marshalls.co.uk/declarations">www.marshalls.co.uk/declarations</a>



## Hawks View Sandstone

### PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Paving Class 1 tolerances to all dimensions as standard, Setts Class 2 tolerances to all dimensions as standard, Kerbs Class 2 tolerances to all dimensions as standard, Others by agreement
Abrasion Resistance (mm)	17mm (Mean value to EN 14157 : 2017) (Hev = 18.34mm)
Durability (Freeze-thaw)	23.3/25 Mpa (Mean values to EN 12371 : 2010)
Material Density	2520 kg/m <sup>3</sup> (Mean value to EN 1936 : 2006)
Open Porosity (%)	3.9% (Mean value to EN 1936 : 2006)
Slip Resistance (Dry)	Blasted 89   Flamed 86   Bush Hammered 90   Clear Blast 95
Slip Resistance (Wet)	Blasted 78   Flamed 62   Bush Hammered 69   Clear Blast 76
Transverse/Flexural Split/Breaking	32.6 MPa (Mean value to EN 12372 : 2022 (Lev = 25 MPa))
LRV Range	Blasted 40.92   Flamed .25   Bush Hammered 32.68   Clear Blast 29.19
Surface Roughness (Rz - µm)	Blasted 56.71   Flamed 76.69   Bush Hammered 129.33   Clear Blast 73.36
Compressive Strength (Mpa)	151 MPa (Mean value to EN 1926 : 2006 (Lev = 85 MPa))
Water Absorption (%)	1.4% (Mean value to EN 13755 : 2008 (Hev = 1.56%))

### SUPPLY

Packaging	Crated
-----------	--------

### FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

