

Larissa Granite



*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Larissa Granite is a versatile and durable stone that offers hard-wearing performance and strength while adding elegance to a wide range of schemes. A light beige colour, Larissa Granite delivers the resilience that granite is known for. Suitable for pedestrian and vehicular trafficked areas, it is available across a wide range of product areas including paving, setts, kerbs, tactile, steps, water management and street furniture. All Marshalls granites are fully tested to the appropriate standards in the UK and where relevant UKCA marked in accordance with the latest legislation.

DESCRIPTION	
Appearance	Buff with black and white and fine silver inclusions
Manufacturing Process	Sawn
Geological Type	Granite
Quarry Location	Shandong Province, China
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012, BS EN 1342 : 2012 & BS EN 1343 : 2012
Petrographical Description	Off white to pale grey and spotted orange coarse grained granite
UKCA Marking/DOP	www.marshalls.co.uk/declarations

Larissa Granite

PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Paving Class 1 tolerances to all dimensions as standard, Setts Class 2 tolerances to all dimensions as standard, Kerbs Class 2 tolerances to all dimensions as standard, Others by agreement
Abrasion Resistance (mm)	16.5mm (Mean value to EN 14157 : 2004 (Hev = 16.5mm))
Durability (Freeze-thaw)	11/12.2 MPa (Mean values to EN 12371 : 2006)
Material Density	2590 kg/m ³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	1.15% (Mean value to EN 1936 : 2006)
Slip Resistance (Dry)	Fine Picked 91
Slip Resistance (Wet)	Fine Picked 77
Transverse/Flexural Split/Breaking	14.3 MPa (Mean value to EN 12372 : 2006 (Lev = 12.6 MPa))
LRV Range	Fine Picked 59.05
Surface Roughness (Rz - µm)	Fine Picked >75
Compressive Strength (Mpa)	169 MPa (Mean value to EN 1926 : 2006 (Lev = 133 MPa))
Water Absorption (%)	0.4% (Mean value to EN 13755 : 2002 (Hev = 0.4%))

SUPPLY

Packaging	Crated
-----------	--------

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233