


Lunar® 600 x 200 x 80



Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

Lunar® is an innovative, contemporary addition to our established concrete paving portfolio, available in a carefully curated range of four colours and five sizes. Developed with UK designers, our unique granite-inspired blends are brought to life through a patented colour application - creating a multi-hued, subtle and elegant aesthetic. Lunar® block pavers are available in a smooth finish with pencil chamfered edges, creating a modern yet timeless classic look, perfect for both pedestrianised and trafficked areas.

Download the **EPD** for Lunar here.

DESCRIPTION	
Appearance	Solid unit with smooth surface
Manufacturing Process	Semi dry pressed & vibrated concrete
Base Raw Material	Concrete
UKCA Marking/DOP	www.marshalls.co.uk/declarations
NBS Specification	Q24/113, Q24/112, Q1/322, Q24/110, Q24/10



Lunar® 600 x 200 x 80

PHYSICAL PROPERTIES

Work Dimensions (mm)	599 x 199 x 80
Nominal Dimensions (mm)	600 x 200 x 80
Tolerances on Work Dimensions (mm)	Class 2 tolerances to all dimensions as standard, Length $\pm 2\text{mm}$, width $\pm 2\text{mm}$, thickness $\pm 3\text{mm}$
Abrasion Resistance (mm)	$\leq 23\text{mm}$ (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	$\leq 1.0 \text{ kg/m}^2$ as a mean with no individual value $> 1.5 \text{ kg/m}^2$
Material Density	2300 kg/m^3 (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45
Thermal Conductivity (K value)	Design data as defined to BS EN 13369 : 2013
Bending Strength MPa	Characteristic bending strength of 5.0 MPa with no individual result less than 4.0 MPa
Transverse/Flexural Split/Breaking	Characteristic bending strength of 5.0 MPa with no individual result less than 4.0 MPa

SPECIFICATION

Approx unit weight (kg)	23
External Fire Performance	Deemed to satisfy when used for roofing
Reaction to fire	Class A1 when used for internal flooring
Installation	Laid in accordance with BS 7533-102:2025

SUSTAINABILITY

Breemam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
---------	---

APPLICATION

Loading Classification	If you require further information please refer to the contact us section.
------------------------	--

SITE WORKS

Coverage	9 no per m^2
----------	-----------------------

SUPPLY

Av. Pack Size m^2	8.64
Units Per Pack	72
Av. pack weight (kg)	1555

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

