Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 05/02/24

Stonespar - Grishma Blend





Marshalls' Stonespar range is a strong and durable sandstone plank paving collection featuring pre-designed colour blends inspired by the four seasons. The Stonespar Grishma Blend contains a mix of complementary beige and buffy hues to create a unique patterned aesthetic. The paving stones come pre-mixed in the crate to ensure speedy installation and reduce space on site. Stonespar paving is suitable for urban areas such as town centres and commercial spaces. Their non-slip properties make them ideal for pedestrianised areas while they can also withstand occasional traffic, such as in spaces where delivery and emergency vehicles require access. Marshalls also offers the chance to blend these stones to your own unique blend so please contact us for further details.

DESCRIPTION	
Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry Location	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012
Petrographical Description	50% Brackendale, 25% Brownridge, 25% Laurel Bank
UKCA Marking/DOP	www.marshalls.co.uk/declarations









Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 05/02/24

Stonespar - Grishma Blend

PHYSICAL PROPERTIES	
Nominal Dimensions (mm)	600 x 130 x 65
Tolerances on Work Dimensions (mm)	Class 1 tolerances to all dimensions as standard
Abrasion Resistance (mm)	17.5mm (Mean value to EN 14157 : 2004 (Hev = 18.1mm))
Durability (Freeze-thaw)	Varies
Material Density	2499 kg/m³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	3% (Mean value to EN 1936 : 2006)
Slip Resistance (Dry)	Blasted 97
Slip Resistance (Wet)	Blasted 71
Transverse/Flexural Split/Breaking	26.6 MPa (Mean value to EN 12372 : 2006 (Lev = 22.2 MPa))
Surface Roughness (Rz - µm)	Blasted 53
Compressive Strength (Mpa)	112 MPa (Mean value to EN 1926 : 2006 (Lev = 183 MPa))
Water Absorption (%)	1.17% (Mean value to EN 13755 : 2008 (Hev = 1.2%))
SUPPLY	
Packaging	Crated

FURTHER INFORMATION	
Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233





