
Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 05/02/24

## Stonespar - Hemant Blend





Marshalls' Stonespar range consists of a selection of durable sandstone plank paving products designed to allow for creativity in a variety of urban settings. The collection features six pre-designed blends inspired by the four seasons. The Stonespar Hermant Blend is a mix of complementary greys, browns and beiges that creates a non-uniform look to add visual interest. Stonespar Hermant has all the non-slip properties associated with sandstone, making it ideal for pedestrian areas. It is strong enough to be deployed in areas of occasional traffic, such as those where delivery and emergency vehicles require access. The blend comes pre-mixed in the crate for ease of installation and to save space on site. The paving is also available as single colours and can be blended to your own unique blend. Please contact us for further details.

DESCRIPTION	
Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry Location	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012
Petrographical Description	10% Sander Red, 45% Thornlake, 45% Laurel Bank
UKCA Marking/DOP	www.marshalls.co.uk/declarations









Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 T: 01422 312000 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 05/02/24

## Stonespar - Hemant Blend

PHYSICAL PROPERTIES	
Nominal Dimensions (mm)	600 x 130 x 65
Tolerances on Work Dimensions (mm)	Class 1 tolerances to all dimensions as standard
Abrasion Resistance (mm)	17.5mm (Mean value to EN 14157 : 2004 (Hev = 18.5mm))
Durability (Freeze-thaw)	Varies
Material Density	2485 kg/m³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	3 % (Mean value to EN 1936 : 2006)
Slip Resistance (Dry)	Blasted 96
Slip Resistance (Wet)	Blasted 71
Transverse/Flexural Split/Breaking	26.6 MPa (Mean value to EN 12372 : 2006 (Lev = 22.2 MPa))
Surface Roughness (Rz - µm)	Blasted 38
Compressive Strength (Mpa)	111 MPa (Mean value to EN 1926 : 2006 (Lev =81 MPa))
Water Absorption (%)	1.91% (Mean value to EN 13755 : 2008 (Hev = 2.03%))
SUPPLY	
Packaging	Crated

FURTHER INFORMATION	
Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233





