

Atlas Textured 60 200x100



Atlas™ delivers a stone aesthetic inspired by Chinese and Portuguese finishes, while maintaining the strength and reliability needed for long-lasting performance block paving.

Featuring a textured surface, a choice of sizes, and two depth options, Atlas offers design versatility across a wide range of commercial projects, providing a cost-effective alternative to natural granite. Available in three versatile neutral grey tones, the range can be used individually or blended to create subtle variation or bold, contrasting paved areas.

Suitable for both pedestrian, light and commercial trafficked areas.

UK manufactured, Atlas features two advanced surface technologies. **SurfaceLock®** is our advanced surface durability technology that locks in colour and provides enhanced protection against UV fading, weathering, and everyday wear, while **CarbonStep®** reduces embodied carbon within the mix without compromising performance.

DESCRIPTION	
Appearance	Solid Unit with a Textured Finish incorporating Marshall's SurfaceLock
Manufacturing Process	Semi-dry pressed & vibrated concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003 (Block)
UKCA Marking/DOP	www.marshalls.co.uk/declarations
NBS Specification	Q24/113, Q24/112, Q1/322, Q24/110, Q24/10



Atlas Textured 60 200x100

PHYSICAL PROPERTIES

Work Dimensions (mm)	198x98x60
Nominal Dimensions (mm)	200x100x60
Tolerances on Work Dimensions (mm)	Class 2 tolerances to all dimensions as standard, Length $\pm 2\text{mm}$, width $\pm 2\text{mm}$, thickness $\pm 3\text{mm}$
Abrasion Resistance (mm)	$\leq 23\text{mm}$ (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	$\leq 1.0 \text{ kg/m}^2$ as a mean with no individual value $> 1.5 \text{ kg/m}^2$
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45
Thermal Conductivity (K value)	Design data as defined to BS EN 13369
Tensile Splitting Strength	Characteristic tensile splitting strength not less than 3.6 MPa. None of the individual results shall be less than 2.9 MPa, nor have a failure load less than 250N/mm of splitting length

SPECIFICATION

Approx unit weight (kg)	2.8
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy when used for roofing

SUSTAINABILITY

Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
--------	---

SUPPLY

Av. Pack Size m2	9.6
Units Per Pack	480
Av. pack weight (kg)	1325

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0333 220 2740

