

## Driveline® Channel 200 x 200 x 65mm



Channel -  
Charcoal

Driveline® Channel can be used to channel water to a soakaway within the property boundary in line with Government legislation. This product co-ordinates with many of the Marshalls Driveway products and a number of other surface materials.

Driveline® Channel can be used to achieve a well-balanced finish on your project. For an innovative alternative to Driveline® Channel, Driveline® Drain is a design led, high performance drainage solution.

### DESCRIPTION

|                                   |  |
|-----------------------------------|--|
| Appearance                        | Solid unit with 10mm dish  |
| Manufacturing Process             | Semi dry pressed & vibrated concrete   |
| Base Raw Material                 | Concrete   |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 1338 : 2003 |
| UKCA Marking/DOP                  | <a href="http://www.marshalls.co.uk/dop">www.marshalls.co.uk/dop</a>           |



# Driveline® Channel 200 x 200 x 65mm

## PHYSICAL PROPERTIES

|                                    |   |
|------------------------------------|---|
| Work Dimensions (mm)               | 198 x 198 x 65  |
| Nominal Dimensions (mm)            | 200 x 200 x 65  |
| Abrasion Resistance (mm)           | ≤ 23mm (Wide Wheel Abrasion Test)   |
| Durability (Freeze-thaw)           | ≤ 1.0 kg/m <sup>2</sup> as a mean with no individual value > 1.5 kg/m <sup>2</sup>  |
| Material Density                   | 2300 kg/m <sup>3</sup> (typically)  |
| Slip/Skid Resistance (polished)    | PSRV > 45   |
| Slip/Skid Resistance (unpolished)  | USRV > 45   |
| Transverse/Flexural Split/Breaking | Characteristic tensile splitting strength not less than 3.6MPa. None of the individual results shall be less than 2.9MPa, nor have a failure load less than 250N/mm of splitting length |

## FURTHER INFORMATION

|                        |  |
|------------------------|--|
| Cleaning & Maintenance | Available on request   |
| Efflorescence          | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking  |
| Weathering             | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures. |
| Product Evolution      | Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice   |
| Contact Us             | For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233  |

## SPECIFICATION

|                           |  |
|---------------------------|--|
| Approx unit weight (kg)   | 7  |
| Emission of Asbestos      | No content                               |
| External Fire Performance | Deemed to satisfy when used for roofing  |
| Reaction to fire          | Class A1 when used for internal flooring |

## SUSTAINABILITY

|                      |      |
|----------------------|------|
| Carbon Footprint     | 3.2  |
| Av. pack weight (kg) | 1321 |

## SUPPLY

