

## Drivesett Natrale® 160 x 160 x 50mm



Natrale - Slate

Drivesett Natrale® uses realistic split stone face profiles to provide a cost effective, hardwearing and practical alternative to natural stone driveways. Available in two popular, warm colour ways and a range of different sizes, the varied selection of block sizes can be used to create a truly unique design for your driveway. For the perfect finish to your project, why not consider Drivesett Argent® Edging to complete the look.

| DESCRIPTION                       |                                                                                |
|-----------------------------------|--------------------------------------------------------------------------------|
| Manufacturing Process             | Semi dry pressed & vibrated concrete                                           |
| Base Raw Material                 | Concrete                                                                       |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 1338 : 2003 |

## Drivesett Natrale® 160 x 160 x 50mm

### PHYSICAL PROPERTIES

|                                    |                                                                                                                                                                                         |
|------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Work Dimensions (mm)               | 158 x 158 x 50                                                                                                                                                                          |
| Nominal Dimensions (mm)            | 160 x 160 x 50                                                                                                                                                                          |
| Abrasion Resistance (mm)           | ≤ 23mm (Wide Wheel Abrasion Test)                                                                                                                                                       |
| Durability (Freeze-thaw)           | ≤ 1.0 kg/m <sup>2</sup> as a mean with no individual value > 1.5 kg/m <sup>2</sup>                                                                                                      |
| Material Density                   | 2300 kg/m <sup>3</sup> (typically)                                                                                                                                                      |
| Slip/Skid Resistance (polished)    | PSRV > 45                                                                                                                                                                               |
| Slip/Skid Resistance (unpolished)  | USRV > 45                                                                                                                                                                               |
| Transverse/Flexural Split/Breaking | Characteristic tensile splitting strength not less than 3.6MPa. None of the individual results shall be less than 2.9MPa, nor have a failure load less than 250N/mm of splitting length |

### SPECIFICATION

|                           |                                          |
|---------------------------|------------------------------------------|
| Approx unit weight (kg)   | 3                                        |
| Emission of Asbestos      | No content                               |
| External Fire Performance | Deemed to satisfy when used for roofing  |
| Reaction to fire          | Class A1 when used for internal flooring |
| Installation              | Laid in accordance with BS7533-102:2025  |

### SUSTAINABILITY

|                  |    |
|------------------|----|
| Carbon Footprint | 13 |
|------------------|----|

### SUPPLY

|                      |        |
|----------------------|--------|
| Av. Pack Size m2     | 10.75  |
| Av. pack weight (kg) | 1235.1 |

### FURTHER INFORMATION

|                        |                                                                                                                                                                                                                                                                                                            |
|------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Cleaning & Maintenance | Available on request                                                                                                                                                                                                                                                                                       |
| Efflorescence          | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking                                                                      |
| Weathering             | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures. |
| Product Evolution      | Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice                                                                                                                                |
| Contact Us             | For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233                                                                                                                                                      |