

## Drivesett® Tegula Original Project Pack



If a classic, high-quality new driveway is what your home is calling out for, look no further than Drivesett® Tegula Original block paving. This range of robust concrete paving stones is one of the UK's most popular driveway choices and renowned for its lasting performance.

Contemporary sizing blended with a subtly distressed finish means it is not just about the substance, it delivers on style too. With a choice of three block sizes and six popular colour blends, this traditional paving option is perfect for creating your dream driveway, no matter how ambitious your design. Drivesett Tegula block paving is the definitive choice. It's one of our most popular products – and it's clear to see why.

All driveways will require some form of edge restraint for long-lasting structural stability, so we've created a range of kerbs to perfectly complement the classic look of Drivesett® Tegula block paving.

Complete your driveway project using Marshall's Joint Filling Sand; a special kiln dried sand suitable for use with all types of block paving and available in two colours - Red and Golden.

DESCRIPTION	
Manufacturing Process	Semi dry pressed & vibrated concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003
NBS Specification	NA

## Drivesett® Tegula Original Project Pack

### PHYSICAL PROPERTIES

Work Dimensions (mm)	240 x 160 x 50 / 160 x 160 x 50 / 120 x 160 x 50
Nominal Dimensions (mm)	238 x 158 x 50 / 158 x 158 x 50 / 118 x 158 x 50
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m <sup>2</sup> as a mean with no individual value > 1.5 kg/m <sup>2</sup>
Material Density	2300 kg/m <sup>3</sup> (typically)
Slip/Skid Resistance (polished)	PSRV > 45
Slip/Skid Resistance (unpolished)	USRV > 45
Transverse/Flexural Split/Breaking	Characteristic tensile splitting strength not less than 3.6MPa. None of the individual results shall be less than 2.9MPa, nor have a failure load less than 250N/mm of splitting length

### SPECIFICATION

Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy when used for roofing
Reaction to fire	Class A1 when used for internal flooring
Installation	Available on request. Keep all units dry before laying & protect incomplete workings during adverse weather or freezing conditions

### SUSTAINABILITY

Carbon Footprint	13
------------------	----

### SUPPLY

Av. Pack Size m <sup>2</sup>	9.73
Units Per Pack	310
Av. pack weight (kg)	1126.7

### FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233