

## Modal X Textured 160x120x60



The Modal X range is available in eight colours, two finishes, 15 plan sizes and five depths including three complementary sett sizes featuring a textured riven surface. The Piora permeable options also offer additional choices of depth and plan sizes. Inspired by the most popular Conservation X and Modal paving ranges, which incorporates the La Linia range, Modal X offers a truly premium, contemporary range.

Modal X gives specifiers higher levels of flexibility when creating landscape designs in mixed-use spaces. Suitable for both pedestrianised and high-traffic areas, Modal X offers a wide range of warm, neutral, and complementary colours. This includes the captivating new pink granite, along with favourites like silver grey and light granite to provide an extensive breadth of choice for contemporary, beautiful designs for all multi-use areas. With versatility at its core, the range offers a mix of different paving formats from modern linear units for delineating public spaces to smaller elements for finer detailing and edging to give spaces character and unique design elements. Locally manufactured in Britain using Marshall's concrete technology, providing a low carbon alternative to granite and cost-effective, flexible installation.

| DESCRIPTION                       |  |
|-----------------------------------|--|
| Appearance                        | Solid Unit with a smooth surface and intergral spacers with Maxi-Mix Technology 4mm Facing layer |
| Manufacturing Process             | Semi dry pressed & vibrated concrete   |
| Base Raw Material                 | Concrete   |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 1338 : 2003                   |
| UKCA Marking/DOP                  | <a href="http://www.marshalls.co.uk/declarations">www.marshalls.co.uk/declarations</a>           |



## Modal X Textured 160x120x60

### PHYSICAL PROPERTIES

|                                    |   |
|------------------------------------|---|
| Work Dimensions (mm)               | 159 x 119 x 60  |
| Nominal Dimensions (mm)            | 160 x 120 x 60  |
| Tolerances on Work Dimensions (mm) | Length $\pm 2$ mm, width $\pm 2$ mm, thickness $\pm 3$ mm   |
| Abrasion Resistance (mm)           | $\leq 23$ mm (Wide Wheel Abrasion Test)   |
| Durability (Freeze-thaw)           | $\leq 1.0$ kg/m <sup>2</sup> as a mean with no individual value $> 1.5$ kg/m <sup>2</sup>   |
| Slip/Skid Resistance (polished)    | Mean polished skid resistance value (PSRV) : $> 45$   |
| Slip/Skid Resistance (unpolished)  | Mean unpolished skid resistance value (USRV) : $> 45$   |
| Thermal Conductivity (K value)     | Design data as defined to BS EN 13369: 2013   |
| Tensile Splitting Strength         | Characteristic tensile splitting strength not less than 3.6 MPa. None of the individual results shall be less than 2.9 MPa, nor have a failure load less than 250N/mm of splitting length |

### SPECIFICATION

|                           |   |
|---------------------------|---|
| Approx unit weight (kg)   | 3   |
| Emission of Asbestos      | No content  |
| External Fire Performance | Deemed to satisfy when used for roofing           |
| Reaction to fire          | Class A, see commission decision 200/553/ECU      |
| Installation              | Laid in accordance with BS EN 7533-3:2005+A1:2009 |

### SUSTAINABILITY

|        |   |
|--------|---|
| Breeam | These units can achieve an "A" rated system when used in conjunction with the correct sub-base components |
|--------|---|

### SITE WORKS

|          |                            |
|----------|----------------------------|
| Coverage | 52.1 no per m <sup>2</sup> |
|----------|----------------------------|

### SUPPLY

|                              |      |
|------------------------------|------|
| Av. Pack Size m <sup>2</sup> | 9.45 |
| Units Per Pack               | 492  |
| Av. pack weight (kg)         | 1228 |

### FURTHER INFORMATION

|                        |   |
|------------------------|---|
| Cleaning & Maintenance | Available on request  |
| Efflorescence          | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking   |
| Weathering             | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.  |
| Product Evolution      | Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details |
| Contact Us             | For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233   |

