

Sylvern® Paving 915 x 610 x 22mm



If you're looking for natural stone paving that looks beautiful and is durable and hard-wearing, then our Sylvern® Limestone paving is a popular choice.

With its natural textured surface it provides a clean and attractive finish, which remains slip resistant even when wet. It comes in a large choice of sizes or a project pack so you can really create your own unique look. Check out our Natural stone patio ideas to give you inspiration before you start.

When installing your Sylvern paving, we recommend using our Paving Primer.

DESCRIPTION	
Appearance	Grey to Grey/Brown with lightly riven surface, fine to very fine grained
Geological Type	Limestone
Quarry Location	Quarries in the Hyderabad district, India
Base Raw Material	Natural Stone
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012

Sylvern® Paving 915 x 610 x 22mm

PHYSICAL PROPERTIES

Work Dimensions (mm)	905 x 600 x 22
Nominal Dimensions (mm)	915 X 610 x 22
Abrasion Resistance (mm)	18.5mm
Material Density	2699.60 kg/m ³ (typically)
Slip/Skid Resistance (polished)	> 45 PSRV
Slip/Skid Resistance (unpolished)	70 USRV
Transverse/Flexural Split/Breaking	22.8 MPa (mean)
Water Absorption (%)	0.13%

SPECIFICATION

Approx unit weight (kg)	31.7
Installation	Available on request. Keep all units dry before laying & protect incomplete workings during adverse weather or freezing conditions

SUPPLY

Av. Pack Size m2	16.74
------------------	-------

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Weathering	Both natural and reconstructed stone products are affected by the action of sunlight and rainfall over time. Weathering It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures. Natural stone may show brown colouration as its iron content oxidises.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233