



Tescina 200 x 100 x 60

Date Created: 03/08/18



*Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

Supplied in a classic size, Tescina Textured Block Paving delivers good looks and excellent structural stability, its textured surface offering enhanced slip-skid performance.

Suitable for use in loading applications including civil, retail, and commercial, the chamfer-free edges of each block provide an easy ride for wheeled traffic, making Tescina an ideal choice for any area which is frequently used by trolleys, prams or wheelchairs.

Tescina is available in 5 colours – Natural, Charcoal, Buff, Brindle and Urban Grey. Select one for a uniform approach to a scheme's aesthetic, or mix and match different colours for delineation and decorative purposes.

DESCRIPTION		
Appearance	Solid unit with textured surface and integral spacers	
Manufacturing Process	Semi dry pressed & vibrated concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003	
CE Marking/DOP	https://www.marshall's.co.uk/dop	
NBS Specification	Q24 110	Q24 112
	Q24 10	Q24 113

Tescina 200 x 100 x 60

Date Created: 03/08/18

PHYSICAL PROPERTIES

Tolerances	Minimum (mm)	Maximum (mm)
Length	198	202
Width	98	102
Thickness	57	63
Work Dimensions (mm)	200 x 100 x 60	
Nominal Dimensions (mm)	200 x 100 x 60	
Tolerances on Work Dimensions (mm)	Length ± 2 mm, width ± 2 mm, thickness ± 3 mm	
Abrasion Resistance (mm)	≤ 23 mm (Wide Wheel Abrasion Test)	
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²	
Material Density	2300 kg/m ³ (typically)	
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45 .	
Thermal Conductivity (K value)	Design data as defined in BS EN 13369 : 2013	

SPECIFICATION

Approx unit weight (kg)	2.8
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY

Breem	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	17 kg CO ₂ m ²

SITE WORKS

Coverage	50 no per m ²
----------	--------------------------

SUPPLY

Av. pack size (m ²)	8.6
Av. pack weight (kg)	1210
Packaging	All packs are shrinkwrapped onto pallets for fork off-load or crane off-load if necessary

APPLICATION

Suitability	Laid in accordance with BS 7533-3 : 2005 + A1 : 2009
-------------	--

FURTHER INFORMATION

Cleaning & Maintenance	Information regarding the cleaning & maintenance of this product may be obtained on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233