


Tegula Priora 240 x 160 x 60

Date Created: 07/02/19



*Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

Marshall's market-leading Priora permeable paving has been proven over 10 years of successfully installed projects. Tegula Permeable Paving is a lightly weathered, multi-size, SuDS-compliant surfacing solution, ideal for use in rural, rustic projects.

The traditional sizes create a classically British aesthetic that suits civic and residential developments alike. Each unit features the unique, patented Priora nib which ensures that surface water drains straight into the specially prepared sub-base, leaving the paved area clean, safe and puddle-free. The nibs also interlock to enhance surface stability.

Tegula Priora is available in 5 different colours and 3 different plan sizes to enable a variety of laying patterns to be created. As long as the sub-base is installed to Marshall's specification, Tegula Priora is suitable for all loading requirements.

DESCRIPTION

Appearance	Solid unit with integral spacers intended to create 6mm drainage apertures
Manufacturing Process	Semi dry pressed & vibrated concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003
CE Marking/DOP	https://www.marshalls.co.uk/dop
NBS Specification	Q24 115



Tegula Priora 240 x 160 x 60

Date Created: 07/02/19

PHYSICAL PROPERTIES

Tolerances	Minimum (mm)	Maximum (mm)
Length	238	242
Width	158	162
Thickness	57	63
Work Dimensions (mm)	240 x 160 x 60	
Nominal Dimensions (mm)	240 x 160 x 60	
Tolerances on Work Dimensions (mm)	Length ±2mm, width ±2mm, thickness ±3mm	
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)	
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²	
Material Density	2300 kg/m ³ (typically)	
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45.	
Thermal Conductivity (K value)	Design data as defined in BS EN 13369 : 2013	
Tensile Splitting Strength	Characteristic tensile splitting strength not less than 3.6 MPa. None of the individual results shall be less than 2.9 MPa, nor have a failure load less than 250N/mm of splitting length	

SPECIFICATION

Approx unit weight (kg)	5.3
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY

Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	16 kg CO ₂ m ²

APPLICATION

Loading Classification	Category 5 - 1 large goods vehicle per week (0.015 msa)
------------------------	---

SITE WORKS

Coverage	17 no per m ²
----------	--------------------------

SUPPLY

Av. pack size (m ²)	9.6
Av. pack weight (kg)	1323
Packaging	All packs are shrinkwrapped onto pallets for fork off-load or crane off-load if necessary

FURTHER INFORMATION

Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details Product Evolution Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233