



## Keykerb KL HB or BN


Date Created: 14/06/18



Keykerb - Grey



Keykerb - Charcoal



Keykerb - Red



Keykerb - Brindle

A range of units designed to perfectly complement Keyblok, the UK's most popular concrete block paving, on schemes where sharp detailing cannot be compromised.

As well as providing a perfect colour match, a full range of ancillary shapes is available including radii, droppers and angle stones, to ensure that each landscape is fully functional as well as visually appealing

DESCRIPTION		
Manufacturing Process	Semi dry pressed & vibrated concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003	
CE Marking/DOP	<a href="https://www.marshall's.co.uk/dop">https://www.marshall's.co.uk/dop</a>	
NBS Specification	Q10 10 Q10 112 Q10 510	Q10 110 Q10 150

## Keykerb KL HB or BN

Date Created: 14/06/18

### PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Length $\pm 2$ mm, width $\pm 2$ mm, thickness $\pm 3$ mm
Abrasion Resistance (mm)	$\leq 23$ mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	$\leq 1.0$ kg/m <sup>2</sup> as a mean with no individual value $> 1.5$ kg/m <sup>2</sup>
Material Density	2300 kg/m <sup>3</sup> (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : $> 45$
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : $> 45$ .
Thermal Conductivity (K value)	Design data as defined to BS EN 13369 : 2013

### SPECIFICATION

Approx unit weight (kg)	5.6
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/EU
Reaction to fire	Class A1, see commission decision 2000/605/EC

### FURTHER INFORMATION

Cleaning & Maintenance	Information regarding the cleaning & maintenance of this product may be obtained on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discoloration known as efflorescence. This is not a product fault and will gradually disappear with exposure to trafficking and weathering. Any product containing cement during its early life may exhibit a temporary white discoloration known as efflorescence. This is not a product fault and will gradually disappear with exposure to trafficking and weathering
Weathering	it should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of the individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice.
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233

