

Keyblok Sett Small 160 x 120 x 60

Date Created: 03/08/18



*Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

An attractive paving solution for walkways, seating areas and even front loading spaces, Keyblok Concrete Sett Paving is a popular choice for any project that needs to combine function with durability and style.

The product is available in 3 traditional sett plan sizes – 160 x 240mm, 160 x 160mm and 160 x 120mm. This allows designers creative freedom to formulate distinct patterns. Alternatively, one sett can be laid on its own to create a uniform look.

Our Keyblok Sett Paving is available in two thicknesses - 60mm setts are able to withstand occasional HGV overrun, while 80mm setts can easily handle heavy duty applications. This durability makes it a popular choice for large public spaces with high volumes of foot and vehicle traffic.

Keyblok Sett Paving is available in a choice of 4 colour options – Brindle, Burnt Ochre, Bracken and Pennant Grey.

DESCRIPTION

Appearance	Solid pencil edged unit with integral spacers	
Manufacturing Process	Semi dry pressed & vibrated concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003	
CE Marking/DOP	https://www.marshall's.co.uk/dop	
NBS Specification	Q24 10 Q24 112	Q24 110 Q24 113

Keyblok Sett Small 160 x 120 x 60

Date Created: 03/08/18

PHYSICAL PROPERTIES

Tolerances	Minimum (mm)	Maximum (mm)
Length	158	162
Width	118	122
Thickness	57	63
Work Dimensions (mm)	160 x 120 x 60	
Nominal Dimensions (mm)	160 x 120 x 60	
Tolerances on Work Dimensions (mm)	Length ± 2 mm, width ± 2 mm, thickness ± 3 mm	
Abrasion Resistance (mm)	≤ 23 mm (Wide Wheel Abrasion Test)	
Chamfer Dimensions	5 mm	
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²	
Material Density	2300 kg/m ³ (typically)	
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45 .	
Thermal Conductivity (K value)	Design data as defined to BS EN 13369 : 2013	

SPECIFICATION

Approx unit weight (kg)	2.5
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY

Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
--------	---

SITE WORKS

Coverage	52 no per m ²
----------	--------------------------

SUPPLY

Av. pack size (m ²)	9.5
Av. pack weight (kg)	1020
Packaging	All packs are shrinkwrapped onto pallets for fork off-load or crane off-load if necessary

APPLICATION

Suitability	Laid in accordance with BS 7533-3 : 2005 + A1 : 2009
-------------	--

FURTHER INFORMATION

Cleaning & Maintenance	Information regarding the cleaning & maintenance of this product may be obtained on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233