


## Bus Stop 180 Drop Kerb LH

Date Created: 07/02/19



Bus Stop Kerb -  
Smooth Grey

Marshall's Bus Stop Kerb is a smooth, angle-faced kerb with the option of channel usage. The channel unit includes a rumble strip, enabling the driver to position the vehicle as close to the kerb as possible. This two-piece system has been designed to provide pedestrians with safe and easy access to buses and similar transportation.

The smooth, angle-faced kerb can be installed at a variety of heights to allow for even the lowest of bus steps. Due to the kerb system construction, varied upstands of between 100-250mm can be achieved for different entry levels of public transport vehicles.

Marshall's bus stop kerbs have users in mind, while at the same time being designed to tolerate bus wheel impact, meaning you can be confident of their durability.

| DESCRIPTION                       |  |                   |
|-----------------------------------|--|-------------------|
| Appearance                        | Solid unit with profiled surface   |                   |
| Manufacturing Process             | Hydraulically pressed concrete   |                   |
| Base Raw Material                 | Concrete   |                   |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 1340 : 2003 |                   |
| NBS Specification                 | Q10 112<br>Q10 510   | Q10 10<br>Q10 110 |

## Bus Stop 180 Drop Kerb LH

Date Created: 07/02/19

### PHYSICAL PROPERTIES

|                                    |   |
|------------------------------------|---|
| Tolerances on Work Dimensions (mm) | Width $\pm 3$ mm, height $\pm 3$ mm, length $\pm 3$ mm                                    |
| Abrasion Resistance (mm)           | $\leq 23$ mm (Wide Wheel Abrasion Test)   |
| Durability (Freeze-thaw)           | $\leq 1.0$ kg/m <sup>2</sup> as a mean with no individual value $> 1.5$ kg/m <sup>2</sup> |
| Material Density                   | 2300 kg/m <sup>3</sup> (typically)  |
| Slip/Skid Resistance (polished)    | Mean polished skid resistance value (PSRV) : $> 45$                                       |
| Slip/Skid Resistance (unpolished)  | Mean unpolished skid resistance value (USRV) : $> 45$ .                                   |

### SPECIFICATION

|                           |   |
|---------------------------|---|
| Emission of Asbestos      | No content  |
| External Fire Performance | Deemed to satisfy. See commission decision 2000/553/ECU |
| Reaction to fire          | Class A1, see commission decision 2000/605/EC           |

### SUSTAINABILITY

|                  |                      |
|------------------|----------------------|
| Carbon Footprint | Available on Request |
|------------------|----------------------|

### FURTHER INFORMATION

|                        |  |
|------------------------|--|
| Cleaning & Maintenance | Cleaning & maintenance details are available on request  |
| Efflorescence          | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking  |
| Weathering             | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.   |
| Product Evolution      | The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice |
| Contact Us             | For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233  |