

Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 https://www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943

E: services.advisory@marshalls.co.uk

## Keyedge 50 x 150 x 800 Buff

Date Created: 07/02/19











For a practical and durable finishing touch, Keyedge Concrete Coloured Edging has been designed specifically for housebuilding applications. Used in conjunction with other products from the Marshalls Keyblok paving and flags collection, they complement and integrate with each other, creating an attractive, unified space outside a new build.

With dimensions of 50mm x 150mm x 800mm and a chamfered profile edge, this edging comes in 4 colours: Bracken, Brindle, Buff and Charcoal. The selected colours work with and contrast against the other Marshalls paving products – no unsightly clashes here.

Whether it's a driveway, a path, a garden or a boundary that requires standout edging, this coloured range is adaptable as part of various housebuilding schemes and styles.

DESCRIPTION	
Appearance	Solid unit with flat surface
Manufacturing Process	Semi dry pressed & vibrated concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1340 : 2003
CE Marking/DOP	https://www.marshalls.co.uk/dop
NBS Specification	Q10 10













BUSINESS IN THE COMMUNITY













Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 https://www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943

E: services.advisory@marshalls.co.uk

Date Created: 07/02/19

## Keyedge 50 x 150 x 800 Buff

PHYSICAL PROPERTIES	
Work Dimensions (mm)	50 x 150 x 800
Tolerances on Work Dimensions (mm)	Width ±3mm, height ±3mm, length ±3mm
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m² as a mean with no individual value > 1.5 kg/m133
Material Density	2300 kg/m³ (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45.
Transverse/FlexuralSplit/Breaking	Characteristic bending strength of 3.5 MPa with no individual result less than 2.8 MPa

SPECIFICATION	
Approx unit weight (kg)	12.6
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY		
Carbon Footprint	Available on Request	

CLIDDLY	
SUPPLY Units Per Pack	16
FURTHER INFORMATION	J
Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233

























