


Fitzroy Masonry & Facades

Date Created: 10/05/18



Fitzroy Polished Granite

Projects looking for a buff stone are ideally served by Fitzroy, which combines impeccable technical performance with beautiful buff tones.

DESCRIPTION	
Geological Type	Granite
Quarry of Origin	Quy Nhon City, Binh Dinh Province, Vietnam
Base Raw Material	Granite
Petrographical Description	Faint Yellow, Pink Beige Background with grey black coarse grained granite
CE Marking/DOP	https://www.marshalls.co.uk/dop



Fitzroy Masonry & Facades

Date Created: 10/05/18

PHYSICAL PROPERTIES

Durability (Freeze-thaw)	13.5/11.3 MPa (Mean values to EN 12371 : 2006)
Material Density	2588 kg/m ³ (typically)
Open Porosity (%)	0.9
Water Absorption (%)	0.37

SPECIFICATION

Reaction to fire	Class A1
------------------	----------

FURTHER INFORMATION

Contact Us

For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233