


## Fletcher Bank Masonry & Facades

Date Created: 10/05/18



Fletcher Bank Swatch

Fletcher Bank is a fine grained stone hailing from a quarry near Ramsbottom, Lancashire. Buff to grey in colouration, Fletcher Bank has been used in all manner of projects across the UK

### DESCRIPTION

Geological Type	Millstone Grit Series, Carboniferous Sandstone
Quarry of Origin	Fletcher Bank Quarry, Lancashire
Base Raw Material	Sandstone
Petrographical Description	Pale grey to pale buff / buff, fine to medium to coarse grained sandstone
CE Marking/DOP	<a href="https://www.marshalls.co.uk/dop">https://www.marshalls.co.uk/dop</a>

# Fletcher Bank Masonry & Facades

Date Created: 10/05/18

## PHYSICAL PROPERTIES

Durability (Freeze-thaw)	4.4/7.3 MPa (Mean values to EN 12371 : 2006)
Material Density	2310 kg/m <sup>3</sup> (typically)
Open Porosity (%)	12.8
Water Absorption (%)	3.6

## SPECIFICATION

Reaction to fire	Class A1
------------------	----------

## FURTHER INFORMATION

### Contact Us

For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233