
Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 0333 000 20 50 www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943 E: advisoryservices@marshalls.co.uk

Malasana Masonry & Facades

Date Created: 23/04/18





A bold red colouration means this Vietnamese stone is bound to make an impact. Whether used as a plinth or a full envelope, Malasaña is the ideal stone for a memorable project

| DESCRIPTION | |
|--------------------------|--|
| Geological Type | Granite/Porphyry |
| Quarry of Origin | Quy Nhon City, Binh Dinh Province, Vietnam |
| Base Raw Material | Granite |
| Petrographical Standards | Red Pink with Grey/Greenish grains coarse grained granite/porphyry |
| CE Marking/DOP | https://www.marshalls.co.uk/dop |



Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 0333 000 20 50 www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943 E: advisoryservices@marshalls.co.uk

Malasana Masonry & Facades

Date Created: 23/04/18

| PHYSICAL PROPERTIES | |
|--------------------------|---|
| Durability (Freeze-thaw) | 19.99/16.4 MPa (Mean values to EN 12371 : 2006) |
| Material Density | 2610 kg/m³ (typically) |
| Open Porosity (%) | 0.6 |
| Water Absorption (%) | 0.22 |

SPECIFICATION

Reaction to fire Class A1

DESIGN GUIDANCE

Technical information Refer to Marshalls online paving design tool www.marshalls.co.uk/commercial/too

lbox/paving-design

FURTHER INFORMATION

Contact Us

For technical information on the design, specification and construction when utilising the product, contact the Technical Advances Services Department

on 0370 411 2233