



## Taksim Granite


Date Created: 26/07/19



Taksim - Fine Picked



Taksim - Flamed



Taksim - Polished

\*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Taksim is a hard wearing pink granite suitable for a variety of applications.

### DESCRIPTION

Appearance	A pale pink to pale pink / grey coarse grained granite
Manufacturing Process	Sawn
Geological Type	Granite
Quarry of Origin	Vietnam
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012, BS EN 1342 : 2012 & BS EN 1343 : 2012
Petrographical Description	A pale pink to pale pink/grey, coarse to very coarse grained granite.
CE Marking/DOP	<a href="https://www.marshalls.co.uk/dop">https://www.marshalls.co.uk/dop</a>

# Taksim Granite

Date Created: 26/07/19

## PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Paving Class 1, Setts Class 2, Kerbs Class 2. Tolerances to all dimensions as standard. Others by agreement Others by agreement
Abrasion Resistance (mm)	16.5mm (Mean value to EN 14157: 2004)
Durability (Freeze-thaw)	13 MPa (Mean value to EN 12372: 2006 (After 56 cycles of Freeze / Thaw to EN 12371: 2010)
Material Density	2630 kg/m <sup>3</sup> (Mean value to EN 1936: 2006)
Open Porosity (%)	0.5% (Mean value to EN 1936: 2006)
Compressive Strength (MPa)	213 MPa (Mean value to EN 1926: 2006 (LEV = 191 MPa))
Water Absorption (%)	0.22% (Mean value to EN 13755: 2008)
Transverse/FlexuralSplit/Breaking	13 MPa (Mean value to EN 12372: 2006 (LEV = 11 MPa))

## TEXTURE SPECIFIC PROPERTIES

	Fine Picked	Flamed	Polished
Surface Roughness (Rz-µm)	>60	>55	--

## MANUFACTURING

Materials Control	CE Marked to EN 1341 (Slabs for Paving), EN 1342 (Setts), EN 1343 (Kerbs)
-------------------	---

## SUSTAINABILITY

ERI Score	Our Score: 3.8 Cluster Score: 2.1
Carbon Footprint	Available on Request

## FURTHER INFORMATION

Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233
------------	---



# Taksim Granite

Date Created: 26/07/19

## Suggested Plan Sizes

