

# Stonespar - Dava Blend

Date Created: 26/07/19



Stonespar - Dava Blend

\*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Marshalls' Stonespar Dava Blend sandstone is designed to provide an extremely durable paving product that can be utilised in a wide range of areas, while also offering a unique, striking design.

With a choice of six pre-designed blends inspired by the four seasons, the Stonespar range is capable of withstanding market place loading. It is perfect for deployment in both pedestrian and trafficked applications, making it the ideal choice for busy urban developments.

Dava Blend is a unique colour mix made up of greys and beiges with a blasted and brushed top surface to improve both colour and anti-slip qualities.

The product is supplied pre-blended, which helps speed up installation time and reduces the space taken up on site.

## DESCRIPTION

Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry of Origin	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012
Petrographical Description	24% Laurel Bank, 11% Thornlake, 65% Marpal Edge
CE Marking/DOP	<a href="https://www.marshalls.co.uk/dop">https://www.marshalls.co.uk/dop</a>



# Stonespar - Dava Blend

Date Created: 26/07/19

## PHYSICAL PROPERTIES

Work Dimensions (mm)	600 x 130 x 65
Tolerances on Work Dimensions (mm)	Class 1 tolerances to all dimensions as standard
Abrasion Resistance (mm)	18mm (Mean value to EN 14157 : 2004 (Hev = 19.8mm))
Durability (Freeze-thaw)	Varies
Material Density	2496 kg/m <sup>3</sup> (Mean value to EN 1936 : 2006)
Open Porosity (%)	4% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	154 MPa (Mean value to EN 1926 : 2006 (Lev = 123 MPa))
Water Absorption (%)	2% (Mean value to EN 13755 : 2008 (Hev = 2.29%))
Transverse/FlexuralSplit/Breaking	28 MPa (Mean value to EN 12372 : 2006 (Lev = 25.46 MPa))

## TEXTURE SPECIFIC PROPERTIES

	Blasted
Surface Roughness (Rz-µm)	38
Slip Resistance (BS 14231) (Dry)	95
Slip Resistance (BS 14231) (Wet)	75

## MANUFACTURING

Materials Control CE Marked to BS EN 1341 Paving

## SUSTAINABILITY

ERI Score Our Score: 3.6  
Cluster Score: 2.4

Carbon Footprint 131.95 kg CO<sub>2</sub> m<sup>2</sup>

## FURTHER INFORMATION

Contact Us For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233



# Stonespar - Dava Blend

Date Created: 26/07/19

## Suggested Plan Sizes



600 x 130

The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.

