Kenfig Sunrise Facing Bricks

Date Created: 28/01/21





This blend of mustard yellow with subtle hints of orange and black hues provide this brick with a bright and cheery appeal and an inviting warmth.

DESCRIPTION		
Manufacturing Process	Vibro-compacted pressed concrete	
Base Raw Material	Concrete	
Green Guide	A+	
CE Marking/DOP	https://www.marshalls.co.uk/dop	
NBS Specification	F10/215	

Date Created: 28/01/21



Kenfig Sunrise Facing Bricks

PHYSICAL PROPERTIES		
Work Dimensions (mm)	215 x 100 x 65	
Nominal Dimensions (mm)	215 x 100 x 65	
Durability (Freeze-thaw)	Frost Resistant	
Gross Density	1960kg/m³	
Thermal Conductivity (K value)	1.11 W/mK (dry); 1.24 W/mK (@3%); 1.33 W/mK (@5%)	
Compressive Strength (MPa)	>22.5N. Air dry	
Water Vapour Permeability	5/15µ (Tabulated from EN 1745)	
Shear Bond Strength	0.15N/mm² (Tabulated from EN 998-2: 2003, Annex C)	
Dimensional Stability	<0.6 mm/m	

	SPECIFICATION	
	Selection Of Mortar	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures
	Emission of Asbestos	No content
	Reaction to fire	Euroclass A1
	Dangerous Substances	No performance declared
	Movement Joints	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures
	Moisture Movement	<0.45mm/m

APPLICATION	
Suitability	Eminently suitable for use below dpc in foundations, boundary walls and externally above ground level up to sulphate resistance class DS2, regardless of the severity of exposure. Manufactured and tested in accordance with BS FN 771-3: 2011+41 2015:

with BS EN 771-3: 2011+A1 2015: Specification for Masonry Units: Aggregate Concrete Masonry Units

SITE WORKS	
Installation	Avaliable on request
SUPPLY	
Packaging	Self-contained packs, non-returnable pallets, with banding straps and polythene stretch hood
No. units per pack	416
FURTHER INFORMATIO	N
Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to

Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking. Our manufacturing process involve the incorporation of advanced additives both within and on the surface of the brick. The amount of efflorescence emanating from the bricks can thus be classed as minimal
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is

	time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	As many of these products are made to

As many of these products are made to order for specific markets, please obtain further details on specification details, product availability, pack sizes and weights from your local Edenhall Sales Office, or alternatively call our Head Office