

Titanium Grey Facing Bricks

Date Created: 28/01/21



Contemporary
Range Titanium
Grey Facing Brick
Swatch Panel

Titanium Grey is a mid grey facing brick with a sand faced texture that provides a modern minimalist feel. This facing brick works well used on its own, but can be used with other colours from our

DESCRIPTION

Manufacturing Process	Vibro-compacted pressed concrete
Base Raw Material	Concrete
Green Guide	A+
CE Marking/DOP	https://www.marshalls.co.uk/dop
NBS Specification	F10/215

Titanium Grey Facing Bricks

Date Created: 28/01/21

PHYSICAL PROPERTIES

Work Dimensions (mm)	215 x 100 x 65
Nominal Dimensions (mm)	215 x 100 x 65
Durability (Freeze-thaw)	Frost Resistant
Gross Density	1920kg/m ³
Thermal Conductivity (K value)	1.11 W/mK (dry); 1.24 W/mK (@3%); 1.33 W/mK (@5%)
Compressive Strength (MPa)	>22.5N. Air dry
Water Vapour Permeability	5/15 μ (Tabulated from EN 1745)
Shear Bond Strength	0.15N/mm ² (Tabulated from EN 998-2: 2003, Annex C)
Dimensional Stability	<0.6 mm/m

SPECIFICATION

Selection Of Mortar	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures
Emission of Asbestos	No content
Reaction to fire	Euroclass A1
Dangerous Substances	No performance declared
Movement Joints	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures
Moisture Movement	<0.45mm/m

APPLICATION

Suitability	Eminently suitable for use below dpc in foundations, boundary walls and externally above ground level up to sulphate resistance class DS2, regardless of the severity of exposure. Manufactured and tested in accordance with BS EN 771-3: 2011+A1 2015: Specification for Masonry Units: Aggregate Concrete Masonry Units
-------------	--

SITE WORKS

Installation	Available on request
--------------	----------------------

SUPPLY

Packaging	Self contained packs, palletised with polythene stretch hood and with or without banding straps dependant on supply works
No. units per pack	396

FURTHER INFORMATION

Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking. Our manufacturing process involve the incorporation of advanced additives both within and on the surface of the brick. The amount of efflorescence emanating from the bricks can thus be classed as minimal
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	As many of these products are made to order for specific markets, please obtain further details on specification details, product availability, pack sizes and weights from your local Edenhall Sales Office, or alternatively call our Head Office