


# Neso Granite

Date Created: 04/05/23



\*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Neso Granite is a strong, hard-wearing and durable stone, suitable for both pedestrian and trafficked spaces.

A versatile stone, it can be used for products including paving, setts, kerbs and steps, water management and street furniture. Specialised and bespoke masonry items may be available on request.

All Marshall's granites are fully tested to the appropriate standards in the UK and where relevant UKCA marked in accordance with the latest legislation

DESCRIPTION	
Appearance	Light beige with Grey Black and Orange inclusions
Manufacturing Process	Sawn
Geological Type	Granite
Quarry of Origin	Villa Real, Portugal
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012, BS EN 1342 : 2012 & BS EN 1343 : 2012
Petrographical Description	White and pale grey with yellow to orange spots coarse Granite
UKCA Marking/DOP	<a href="https://www.marshalls.co.uk/declarations">https://www.marshalls.co.uk/declarations</a>

# Neso Granite

Date Created: 04/05/23

## PHYSICAL PROPERTIES

Work Dimensions (mm)	450 x 450 x 50
	450 x 450 x 60
	450 x 450 x 70
	900 x 450 x 50
	900 x 450 x 60
	900 x 450 x 70
	600 x 600 x 50
	600 x 600 x 60
	600 x 600 x 70
	900 x 600 x 50
	900 x 600 x 60
	900 x 600 x 70
	200 x 100 x 50
	200 x 100 x 60
	200 x 100 x 70
	300 x 100 x 50
	300 x 100 x 60
	300 x 100 x 70
	300 x 150 x 50
	300 x 150 x 60
300 x 150 x 70	
300 x 200 x 50	
300 x 200 x 60	
300 x 200 x 70	

Abrasion Resistance (mm) 20.5mm (Mean value to EN 14157 : 2017 (Hev = 21.06mm))

Durability (Freeze-thaw) 11.4/10.3 MPa (Mean values to EN 12372 : 2006)

Material Density 2572 kg/m<sup>3</sup> (Mean value to EN 1936 : 2006)

Open Porosity (%) 2.23% (Mean value to EN 1936 : 2006)

Compressive Strength (MPa) 63.03 MPa (Mean value to EN 1926 : 2006 (Lev = 63.46 MPa))

Water Absorption (%) 0.8% (Mean value to EN 13755 : 2008 (Hev = 0.85%))

Transverse/FlexuralSplit/Breaking 9.45 MPa (Mean value to EN 12372 : 2022 (Lev = 7.04 MPa))

## TEXTURE SPECIFIC PROPERTIES

Blasted

Light Reflectance Value (LRV) 44.81

Surface Roughness (Rz-µm) >173.58

Slip Resistance (BS 14231) (Dry) 93

Slip Resistance (BS 14231) (Wet) 78

## MANUFACTURING

Materials Control UKCA Marked to BS EN 1341 Paving

## SUSTAINABILITY

ERI Score Our Score: 4.2  
Cluster Score: 3.6


## FURTHER INFORMATION

Contact Us For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

# Neso Granite

Date Created: 04/05/23

## Suggested Plan Sizes



The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.

---