


## Stonespar - Vasanta Blend

Date Created: 22/02/21



Stonespar - Vasanta Blend

\*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

The Marshalls Stonespar range of plank type paving is manufactured from a strong and durable sandstone that makes for the ideal paving solution for urban applications.

It has high-quality, non-slip properties that makes it a great choice for pedestrian use, while durability of the sandstone means it can handle occasional heavier loads from delivery and emergency vehicle loading.

The Vasanta Blend of colours is inspired by the first Spring sunshine of the year. It mixes a base colour of Jayrum Light with a range of other shades to create a unique blend. Colour blends come pre-mixed in the crates to make for a faster and easier installation process.

Other pre-blended mixes in a variety of colours are available, as well as single colours for uniformity in projects, meaning Stonespar has the versatility to suit any application.

DESCRIPTION	
Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry of Origin	Kota Region, Rajasthan, India
Petrographical Description	50% Brackendale, 25% Thornlake, 25% Laurel Bank
CE Marking/DOP	<a href="https://www.marshalls.co.uk/dop">https://www.marshalls.co.uk/dop</a>

# Stonespar - Vasanta Blend

Date Created: 22/02/21

## PHYSICAL PROPERTIES

Work Dimensions (mm)	600 x 130 x 65
Abrasion Resistance (mm)	17.5mm (Mean value to EN 14157 : 2004 (Hev = 18.1mm))
Durability (Freeze-thaw)	Varies
Material Density	2557 kg/m <sup>3</sup> (Mean value to EN 1936 : 2006)
Open Porosity (%)	3.31% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	112 MPa (Mean value to EN 1926 : 2006 (Lev = 183 MPa))
Water Absorption (%)	1.17% (Mean value to EN 13755 : 2008 (Hev = 1.2%))
Transverse/FlexuralSplit/Breaking	30.80 MPa (Mean value to EN 12372 : 2006 (Lev = 25.82 MPa))

## TEXTURE SPECIFIC PROPERTIES

	Blasted
Surface Roughness (Rz-µm)	38
Slip Resistance (BS 14231) (Dry)	96
Slip Resistance (BS 14231) (Wet)	71

## MANUFACTURING

Materials Control UKCA Marked to BS EN 1341 Paving

## SUSTAINABILITY

ERI Score Our Score: 3.6  
Cluster Score: 2.4

## FURTHER INFORMATION

Contact Us For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

# Stonespar - Vasanta Blend

Date Created: 22/02/21

## Suggested Plan Sizes



600 x 130

The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.

---