


Dorado Granite

Date Created: 22/02/21



*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Marshalls' Dorado Granite is a hard-wearing, strong and durable granite suitable for both pedestrian and vehicular trafficked areas.

Predominantly light to mid-grey, Dorado Granite is available in 3 finish options – blasted, flamed and polished – to match different applications and their needs, whether they call for a smooth aesthetic or superior non-slip properties.

It is available across all product areas including Paving, Setts, Kerbs, Tactile, Steps, Water Management, Bespoke Street furniture, Masonry & Specials – allowing for the creation of unified schemes.

Dorado Granite, like all Marshalls Granites, is produced to ISO9001 quality assurance standards and fully tested to the appropriate standards in the UK, as well as being CE marked in accordance with the latest legislation.

DESCRIPTION	
Appearance	Grey white background with black inclusions
Manufacturing Process	Sawn
Geological Type	Granite
Quarry of Origin	Corvaceira, Portugal
Petrographical Description	Pale grey to greyish white Granite with occasional black fine irregular biotite mica.
CE Marking/DOP	https://www.marshalls.co.uk/dop

Dorado Granite

Date Created: 22/02/21

PHYSICAL PROPERTIES

Work Dimensions (mm)	450 x 450 x 50
	600 x 600 x 50
	900 x 600 x 50
	200 x 100 x 50
	300 x 150 x 50
	300 x 200 x 50
	450 x 450 x 60
	900 x 450 x 60
	600 x 600 x 60
	900 x 600 x 60
	200 x 100 x 60
	300 x 100 x 60
	300 x 150 x 60
	300 x 200 x 60
	900 x 600 x 70
	200 x 100 x 70
	300 x 100 x 70
	300 x 150 x 70
	300 x 200 x 70
	450 x 450 x 70
900 x 450 x 50	
900 x 450 x 70	
600 x 600 x 70	
300 x 100 x 50	
Abrasion Resistance (mm)	15.5mm (Mean value to EN 14157 : 2004 (Hev = 16mm))
Durability (Freeze-thaw)	15.9/14.7 MPa (Mean values to EN 12371 : 2006)
Material Density	2630 kg/m ³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	0.7% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	179 MPa (Mean value to EN 1926 : 2006 (Lev = 147 MPa))
Water Absorption (%)	0.3% (Mean value to EN 13755 : 2008 (Hev = 0.3%))
Transverse/FlexuralSplit/Breaking	15.9 MPa (Mean value to EN 12372 : 2006 (Lev = 15.1 MPa))

MANUFACTURING

Materials Control	UKCA Marked to BS EN 1341 Paving, 1342 Setts, 1343 Kerbs
-------------------	--

SUSTAINABILITY

ERI Score	Our Score: 4.2 Cluster Score: 3.6
-----------	--------------------------------------

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233


TEXTURE SPECIFIC PROPERTIES

	Flamed	Polished	Blasted
Slip Resistance (BS 14231) (Dry)	92	55	93
Slip Resistance (BS 14231) (Wet)	73	7	81

Dorado Granite

Date Created: 22/02/21

Suggested Plan Sizes



The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.
