


Stonespar - Sharad Blend

Date Created: 19/01/22



Stonespar - Sharad Blend

*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

The Stonespar Sharad Blend is a style of plank paving used for both its strong technical performance and versatile design capabilities that gives planners greater creative freedom.

The product is available as a Sharad Blend, which mixes the base colour of Ranya Brown with lighter tones to create a unique patterned aesthetic. Colour blends come pre-mixed in crates to aid ease and speed of installation.

Suitable for areas with only occasional delivery and emergency vehicle access, the non-slip qualities of the product makes it perfect for pedestrian traffic. The top surface is blasted and brushed to improve both grip and colour.

Stonespar is a durable sandstone designed to stand the test of time in any modern urban project, combining performance and aesthetics.

DESCRIPTION

Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry of Origin	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012
Petrographical Description	10% Sander Red, 60% Brownridge, 30% Laurel Bank
UKCA Marking/DOP	https://www.marshalls.co.uk/declarations

Stonespar - Sharad Blend

Date Created: 19/01/22

PHYSICAL PROPERTIES

Work Dimensions (mm)	600 x 130 x 65
Abrasion Resistance (mm)	17.5mm (Mean value to EN 14157 : 2004 (Hev = 18.5mm))
Durability (Freeze-thaw)	Varies
Material Density	2485 kg/m ³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	3.49% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	111 MPa (Mean value to EN 1926 : 2006 (Lev =81 MPa))
Water Absorption (%)	1.91% (Mean value to EN 13755 : 2008 (Hev = 2.03%))
Transverse/FlexuralSplit/Breaking	26.6 MPa (Mean value to EN 12372 : 2006 (Lev = 22.2 MPa))

TEXTURE SPECIFIC PROPERTIES

	Blasted
Surface Roughness (Rz-µm)	55
Slip Resistance (BS 14231) (Dry)	97
Slip Resistance (BS 14231) (Wet)	71

MANUFACTURING

Materials Control UKCA Marked to BS EN 1341 Paving

SUSTAINABILITY

ERI Score Our Score: 3.6
 Cluster Score: 2.4


FURTHER INFORMATION

Contact Us For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

Stonespar - Sharad Blend

Date Created: 19/01/22

Suggested Plan Sizes



600 x 130

The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.
