Prospero Granite

T: 01422 312000 F: 01422 312943 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 19/01/22





*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Prospero Granite is a durable, hard-wearing medium grey stone. Like all Marshalls' granites, it features sawn sides and is available in flamed, finepicked and polished finishes.

It is available for all product areas such as paving, setts, kerbs, tactile, steps, water management, street furniture or other bespoke specialised masonry items such as veneers for planters or furniture.

Prospero flame textured or fine picked granite is suitable for both pedestrian or vehicular trafficked areas. Its darker polished version can complement any public space as street furniture, copings and masonry elements.

All Marshalls granites are fully tested to the appropriate standards in the UK and where relevant UKCA marked in accordance with the latest legislation. Granites are generally hard-wearing, strong and durable landscaping materials.

DESCRIPTION	
Appearance	Grey with fine black and white inclusions
Manufacturing Process	Sawn
Geological Type	Diorite / Granodiorite
Quarry of Origin	Fujian Province, China
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012, BS EN 1342 : 2012 & BS EN 1343 : 2012
Petrographical Description	Medium to coarse grained pale grey blueish Diorite/Granodiorite
UKCA Marking/DOP	https://www.marshalls.co.uk/declarations

Prospero Granite

PHYSICAL PROPERTIES	
Work Dimensions (mm)	$\begin{array}{c} 450 \times 450 \times 50 \\ 450 \times 450 \times 60 \\ 450 \times 450 \times 70 \\ 900 \times 450 \times 50 \\ 900 \times 450 \times 60 \\ 900 \times 450 \times 70 \\ 600 \times 600 \times 50 \\ 600 \times 600 \times 60 \\ 600 \times 600 \times 70 \\ 900 \times 600 \times 50 \\ 900 \times 600 \times 50 \\ 900 \times 600 \times 70 \\ 900 \times 600 \times 70 \\ 200 \times 100 \times 50 \\ 200 \times 100 \times 50 \\ 200 \times 100 \times 50 \\ 300 \times 150 \times 70 \\ 300 \times 200 \times 50 \\ 300 \times 200 \times 70 \\$
Abrasion Resistance (mm)	16mm (Mean value to EN 1341 : 2012 (Hev =16.5mm))
Durability (Freeze-thaw)	20.4/20.4 MPa (Mean values to EN 12371 : 2006)
Material Density	2836 kg/m³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	0.50% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	110 MPa (Mean value to EN 1926 : 2006 (Lev = 89.61 MPa))
Water Absorption (%)	0.21% (Mean value to EN 13755 : 2008 (Hev =0.24%))
Transverse/FlexuralSplit/Breaking	18.22 MPa (Mean value to EN 12372 : 2006 (Lev = 16.66 MPa))

TEXTURE SPECIFIC PROPERTIES Flamed Fine Picked Polished Light Reflectance Value 10.47 24.99 34.49 (LRV) Surface Roughness 6 49.7 >75 (Rz-µm) Slip Resistance 00 (E

(BS 14231) (Dry)	22	92	90
Slip Resistance (BS 14231) (Wet)	15	72	78

T: 01422 312000 F: 01422 312943 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 19/01/22

MANUFACTURING	
Materials Control	UKCA Marked to BS EN 1341 Paving
SUSTAINABILITY	
ERI Score	Our Score: 1.9 Cluster Score: 1.1
FURTHER INFORMATION	J
Cleaning & Maintenance	Available on request
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233




Landscape House, Premier Way,T: 01422 312000Lowfields Business Park,F: 01422 312943Elland HX5 9HTE: grouptechnicatTel: 03704 11 22 33W: www.marsha

T: 01422 312000 F: 01422 312943 E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Prospero Granite

Date Created: 19/01/22



The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.