

Danygraig Road, Risca,

T: 01422 312000 F: 01422 312943 Newport NP11 6DP

E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Knightsbridge Stock

Date Created: 18/05/23





A delicate orange/buff facing brick with the added asthetic of a stock face apperance. Knightsbridge stock is part of the stock range of frogged bricks. A stunning range of sustainable facing brick products brought to you by Marshalls Bricks and Masonry.

DESCRIPTION	
Manufacturing Process	Vibro-compacted pressed concrete
Base Raw Material	Concrete
Green Guide	A+
UKCA Marking/DOP	https://www.marshalls.co.uk/declarations

Danygraig Road, Risca, T: 01422 312000 F: 01422 312943

Newport NP11 6DP E: grouptechnicalservices@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 18/05/23

Knightsbridge Stock

PHYSICAL PROPERTIES	
Work Dimensions (mm)	215 x 100 x 65
Nominal Dimensions (mm)	215 x 100 x 65
Durability (Freeze-thaw)	Frost Resistant
Gross Density	1920kg/m³
Thermal Conductivity (K value)	1.11 W/mK (dry); 1.24 W/mK (@3%); 1.33 W/mK (@5%)
Compressive Strength (MPa)	>22.5MPa. Air dry
Water Vapour Permeability	5/15μ (Tabulated from EN 1745)
Shear Bond Strength	0.15N/mm² (Tabulated from EN 998-2: 2003, Annex C)
Dimensional Stability	<0.6 mm/m
SPECIFICATION	
Selection Of Mortar	It is recommended that the guidelines provided in BS EN 1996 - Design of Masonry Structures be taken into account before a final choice is made
Emission of Asbestos	No content
Reaction to fire	Euroclass A1
Dangerous Substances	No performance declared
Movement Joints	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures
Moisture Movement	<0.45mm/m
SUSTAINABILITY	1.602
Carbon Footprint	kg CO2
APPLICATION	
Suitability	Eminently suitable for use below dpc in foundations, boundary walls and externally above ground level up to sulphate resistance class DS2, regardless of the severity of exposure. Manufactured and tested in accordance

with BS EN 771-3: 2011+A1 2015: Specification for Masonry Units: Aggregate Concrete Masonry Units

SITE WORKS	
Installation	Avaliable on request
SUPPLY	
Units Per Pack	396
Packaging	Self contained packs, palletised with polythene stretch hood and with or without banding straps dependant on supply works
FURTHER INFORMATION	
	Cleaning 9 maintenance details are
Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking. Our manufacturing process involve the incorporation of advanced additives both within and on the surface of the brick. The amount of efflorescence emanating from the bricks can thus be classed as minimal
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards
Contact Us	As many of these products are made to order for specific markets, please obtain further details on specification details, product availability, pack sizes and weights from the Marshalls Bricks &

Masonry Sales Team bricksbm@marshalls.co.uk, or alternatively call 01633 600 806