


Tactile Cycleway 400 x 400 x 50



Marshalls Cycleway Tactile Flag Paving is used to indicate the beginning or end of shared pedestrian/cycle routes which are not separated by different levels. It is also used as a central delineation strip running the length of the shared route to provide a false kerb for visually impaired pedestrians.

Guidance states:

- Laid transverse to denote the pedestrian path
- Laid longitudinal to denote the cycle path

Marshalls Cycleway Demarcation Flag Paving is used to alert pedestrians, including the visually impaired, to the proximity of a cycleway. It provides a visual and physical indication on the position of the central limit to cyclists and a visual and detectable underfoot warning to pedestrians.

DESCRIPTION	
Manufacturing Process	Hydraulically pressed concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant manufactured, but not in compliance, to BS EN 1339 : 2003, as the tactility of paving is excluded from the Scope
NBS Specification	Q25 320



Tactile Cycleway 400 x 400 x 50

PHYSICAL PROPERTIES

Work Dimensions (mm)	398 x 398 x 50
Nominal Dimensions (mm)	400 x 400 x 50
Tolerances on Work Dimensions (mm)	Length ± 2 mm, width ± 2 mm, thickness ± 3 mm
Abrasion Resistance (mm)	≤ 23 mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²
Material Density	2300 kg/m ³ (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45
Thermal Conductivity (K value)	Design data as defined to BS EN 13369: 2013
Bending Strength MPa	Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa

SPECIFICATION

Approx unit weight (kg)	19
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY

Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	13 kg CO ₂ m ²

APPLICATION

Loading Classification	Category 1 - Pedestrian and domestic driveways
------------------------	--

SITE WORKS

Coverage	6.25 no per m ²
----------	----------------------------

SUPPLY

Av. Pack Size m ²	5.8
Units Per Pack	36
Av. pack weight (kg)	684

FURTHER INFORMATION

Cleaning & Maintenance	Available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233

