


Tactile Lambeth 600 x 600 x 75



Marshall's Lambeth Tactile Paving has a range of uses and applications in both industrial and public areas. Whether it's to warn pedestrians to stay away from a designated area via the use of raised paving or to stop vehicular access to dangerous or restricted areas, the high-relief pyramid patterning sends a clear message.

Providing traction and grip where required, Lambeth Tactile is ideal for access ramps and steep inclines. It also acts as a vital warning to the visually impaired in key urban areas and works to steer pedestrians away from potential hazards.

Supplied in a 600 x 600mm plan size, please note that this product shouldn't be used in areas that will be exposed to de-icing salts.

| DESCRIPTION | |
|-----------------------------------|--|
| Appearance | Solid unit with profiled surface |
| Manufacturing Process | Semi dry pressed & vibrated concrete |
| Base Raw Material | Concrete |
| Governing Manufacturing Standards | In-house Company Specification |
| UKCA Marking/DOP | www.marshalls.co.uk/declarations |
| NBS Specification | Q25 320 |



Tactile Lambeth 600 x 600 x 75

PHYSICAL PROPERTIES

| | |
|------------------------------------|---|
| Work Dimensions (mm) | 598 x 598 x 68 |
| Nominal Dimensions (mm) | 600 x 600 x 68 |
| Tolerances on Work Dimensions (mm) | Length ± 2 mm, width ± 2 mm, thickness ± 3 mm |
| Abrasion Resistance (mm) | ≤ 23 mm (Wide Wheel Abrasion Test) |
| Durability (Freeze-thaw) | ≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ² |
| Material Density | 2300 kg/m ³ (typically) |
| Slip/Skid Resistance (polished) | Mean polished skid resistance value (PSRV) : > 45 |
| Slip/Skid Resistance (unpolished) | Mean unpolished skid resistance value (USRV) : > 45 |
| Thermal Conductivity (K value) | Design data as defined to BS EN 13369: 2013 |
| Bending Strength MPa | Characteristic bending strength of 5.0 MPa with no individual result less than 4.0 MPa |

SPECIFICATION

| | |
|---------------------------|---|
| Approx unit weight (kg) | 44 |
| Emission of Asbestos | No content |
| External Fire Performance | Deemed to satisfy. See commission decision 2000/553/ECU |
| Reaction to fire | Class A1, see commission decision 2000/605/EC |

SUSTAINABILITY

| | |
|------------------|--------------------------------------|
| Carbon Footprint | 20 kg CO ₂ m ² |
|------------------|--------------------------------------|

APPLICATION

| | |
|-----------------------------|---|
| Loading Classification | Category 1 - Pedestrian and domestic driveways |
| Loading Classification Note | The loading classification details above are specific to this product and plan size. For additional guidance on bond patterns and sub-base designs, please contact Technical Advisory Services Department on 0370 411 2233. |

SITE WORKS

| | |
|----------|---------------------------|
| Coverage | 2.8 no per m ² |
|----------|---------------------------|

SUPPLY

| | |
|------------------------------|---|
| Av. Pack Size m ² | 5.8 |
| Units Per Pack | 16 |
| Av. pack weight (kg) | 704 |
| Packaging | All packs are suitable for crane off-load |

FURTHER INFORMATION

| | |
|------------------------|---|
| Cleaning & Maintenance | Available on request |
| Efflorescence | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking |
| Weathering | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures |
| Product Evolution | Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. |
| Contact Us | For technical information on the design, specification and construction when utilising the product, contact Group Technical Services on 0370 411 2233 |

