

T: 01633 600 806 E: wallingbm@marsalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 20/05/24

Darlstone Split Walling 450 x 100 x 140













We provide a broad range of reconstructed stone walling products that are often used in areas of traditional stone walling, as an alternative to quarried stone and is approved as such for use in National Parks and conservation areas.

Our Cromwell, Darlstone, Thistlestone and Epoch products are available in a variety of colours, from buffs, to browns, and a range of finishes to ensure our products blend easily with vernacular stonework, creating beautiful finished aesthetics for that all important kerb appeal. Bespoke colours can be developed and offered for specific schemes.

As well as housebuilding, our walling is suitable for, and used in a variety of landscaping commercial projects and applications.

Available from stock in full loads or mixed loads with bricks.

| DESCRIPTION | |
|--------------------------------------|---|
| Manufacturing Process | Hydraulically pressed concrete |
| Base Raw Material | Concrete |
| Governing Manufacturing Standards | All data where relevant to be established in accordance with BS EN 771-5 : 2011 + A1 : 2015 |
| UKCA Marking/DOP | www.marshalls.co.uk/declarations |
| NBS Specification | F10/295 |









E: wallingbm@marsalls.co.uk
W: www.marshalls.co.uk/commercial

T: 01633 600 806

Date Created: 20/05/24

Darlstone Split Walling 450 x 100 x 140

ः

Marshalls

Creating Better Spaces

| • | • |
|--------------------------------|---|
| PHYSICAL PROPERTIES | |
| Work Dimensions (mm) | 448x98x140 |
| Nominal Dimensions (mm) | 450x100x140 |
| Durability (Freeze-thaw) | Frost resistant |
| Material Density | 2250 kg/m³ (typically) |
| Thermal Conductivity (K value) | 1.11 (dry), 1.24 (@3%), 1.33 (@5%) |
| Water Vapour Permeability (?) | 5/15 (Tabulated from EN1745) |
| Shear Bond Strength (N/mm2) | 0.15 (Tabulated from EN998- 2:2003 Annex C) |
| Dimensional Stability | 0.6 |
| Water Absorption (%) | 7 to 11 after 24 hours |
| SPECIFICATION | |
| Emission of Asbestos | No Content |
| Reaction to fire | Class A1, see commission decision 2000/605/EC |
| Selection Of Mortar | It is recommended that the guidelines provided in BS EN 1996 - Design of Masonry Structures be taken into account before a final choice is made |
| Dangerous Substances | No performance declared |
| Movement Joints | Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures |
| SUSTAINABILITY | |
| Carbon Footprint | 0 |
| APPLICATION | |
| Suitability | Suitable for general walling projects, given correct structural design in accordance with BS EN 1996 - Design of masonry |

| FURTHER INFORMATION | |
|---------------------------|--|
| Cleaning & Maintenance | Cleaning & maintenance details are available on request |
| Efflorescence | Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking |
| Weathering | It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures |
| Product Evolution | The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details Product Evolution Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice |
| Contact Us | marshallsedenhall@marshalls.co.uk |







structures